

## FILM UV IR EVA AD

PROPERTIES	VALUE	UNIT	NORM
Thickness	150	microns	ISO 4591
Aspect	Normal		EN 13206

### Mechanical Properties

#### Tensile Strength at Break

MD	24 (>16)	MPa	EN ISO 527-3
TD	23 (>16)	MPa	EN ISO 527-3

#### Elongation at Break

MD	670 (>300)	%	EN ISO 527-3
TD	780 (>300)	%	EN ISO 527-3

#### Tensile Strength at Yield

MD	11	MPa	EN ISO 527-3
TD	10	MPa	EN ISO 527-3

#### Creep MD

15	%	EN 13206
----	---	----------

#### Dart Test F 50

Side	600 (>300)	cN	ISO 7765-1
Fold	330 (>190)	cN	ISO 7765-1

### Optical Properties

Total Transmission of Visible Light	93	%	EN 2155-5
Diffusion	54	%	EN 2155-9
Thermal Effect	83	%	EN 13206

### Other Properties

Lifetime (*)	2	Years
--------------	---	-------

#### Additional Properties

--

(\*) At a climate of: 150 kLys/year (for different radiation conditions or different thickness, we should be consulted).